



Olbernhauer Eisenhof GmbH

Am Walzwerk 4 • D-09526 Olbernhau
Tel. (03 73 60) 6955-10 Fax (03 73 60) 6955-20
info@eisenhof.com • www.eisenhof.com

Edelstahl - Werkstoffe - Analysen

Werkstoffe

W.-Nr.:	DIN	AISI (TP)	SIS (14)	AFNOR	BS (GR)
1.4301	x5 CrNi 18 10	304	2333		
1.4306	x2 CrNi 19 11	304 L	2352	Z6CN 18- 9	304 S 15
1.4541	x6 CrNiTi 18 10	321	2337	Z2CN 18-10	304 S 12
1.4571	x6 CrNiMoTi 17 12 2	316 Ti	2350	Z6CNT 18-11	321 S 12
1.4401	x5 CrNiMo 17 12 2	316	2343	Z8CNDT 17-12	320 S 17
1.4404	x2 CrNiMo 17 13 2	316 L	2347	Z6CND 17-11	316 S 16
1.4436	x5 CrNiMo 17 13 3	316	2343	Z2CND 17-12	316 S 12
1.4435	x2CrNiMo 1814 3	316 L	2353	Z6CND 17-12 Z2CND 17-13	316 S 16 316 S 12

Analyse

W.-Nr.:	C max	C %	Ni %	Mn max.%	Si max.%	S max.%	Mo max.%	Ti %
1.4301	0,07	17,0 - 19,0	8,5 - 10,0	2,0	1,0	0,03	-	-
1.4305	0,12	17,0 - 19,0	8,5 - 10,0	2,0	1,0	0,15 - 0,35	-	-
1.4306	0,03	18,0 - 20,0	10,0 - 12,5	2,0	1,0	0,03	-	-
1.4541	0,08	17,0 - 19,0	9,0 - 12,0	2,0	1,0	0,03	-	5 x % C
1.4571	0,08	16,5 - 18,5	10,5 - 13,5	2,0	1,0	0,03	2,0 - 2,5	5 x % C
1.4401	0,07	16,5 - 18,5	10,5 - 13,5	2,0	1,0	0,03	2,0 - 2,5	-
1.4404	0,03	16,5 - 18,5	11,0 - 14,0	2,0	1,0	0,03	2,0 - 2,5	-
1.4436	0,07	16,5 - 18,5	11,0 - 14,0	2,0	1,0	0,03	2,0 - 3,0	-
1.4435	0,03	17,0 - 18,5	12,5 - 15,0	2,0	1,0	0,03	2,5 - 3,0	-

Auf Anfrage

Hitzebeständige Bleche

Werkstoffe: 1.4713, 1.4742, 1.4828, 1.4878

Bleche in Groß-Lager Formaten bis

2500 x 8000 mm

sowie weitere Qualitäten.

**Warmgewalzte Bleche sowie Tränenbleche, auch Großlagerformate
Coils, Spaltbänder, Zuschnitte in allen Ausführungen**